


PREPARED BY  
HIGHWAY PLANNING SURVEY  
IN COOPERATION WITH  
U. S. PUBLIC ROADS ADMINISTRATION

STATE OF MINNESOTA  
DEPARTMENT OF HIGHWAYS  
ROAD LIFE STUDIES  
CONSTRUCTION PROJECT LOG RECORD

CONTROL SECTION 3410  
TRUNK HIGHWAY 55  
COUNTY Kandiyohi  
DISTRICT 3B

LIMITS: N. Co. Line - E. Co. Line.



YEAR BUILT	PROJECT N <sup>o</sup>	DESCRIPTION			CODE N <sup>o</sup>		
		TYPE	WIDTH	THICKNESS			
		Gravel	22'	1"	No Record of Constr. Added in 1934.	1	9.20 Relocation shortens 3.17
1936	55-142-24-1A	Grading Br. 5546	32'		150' B.S.	2	6.03
1937	55-142-24-1A	Stab. Gravel	32'	2-4"	80% Grav. & 20% Binder Soil.	3	6.03
1938	3410-01	Mixed Bit.	24'	1 3/4"		4	6.03
M	1940	A.F.E. 9			Rd. Tar 3889 Gal./Mi. Grav. 132 C.Y./Mi. Maint. Dept.	5	6.03
M	1944	3410-05	Gravel Lifts	34'		6	0.13 0.22
M	1945	A.F.E. 4 A.F.E. 16	Spot Treat. Bit. Surf. Repair		RT-6, 983 Gal./Mi. Grav. 8 C.Y./Mi. Maint. Div.	7	6.03
M	1946	A.F.E. 4	Spot Treat. Bit. Surf. Repair		RT-4, 650 Gal. Agg. 39 C.Y.	8	6.03 (Net 0.10)
C	1947	A.F.E. 17	Bit. Resurfacing Mixed Bit	26'	MC-3, 51959 Gal. Agg. 4207 Tons Added	9	6.03
M	1949	A.F.E. 5	Bit. Seal Coat	26'	RC-3, 11873 Gal. Agg. 465 C.Y.	10	6.03
M	1955	A.F.E. 604	Spot Treat. Bit. Surf. Repair	24'	MC-3, 2929 Gal. Agg. 252 Tons	11	6.03 (Net 0.36)
M	1957	A.F.E. 604	Spot Treat. Bit. Surf. Repair	24'	MC-3, 3686 Gal. Agg. 315 Tons	12	6.03 (Net 0.41)
M	1958	A.F.E. 604	Spot Treat. Bit. Surf. Repair	24'	SC-4, 2912 Gal. Agg. 252 Tons	13	6.03 (Net 0.34)
C	1960	3410-08	Grading Gravel Base Road Mix Bit	42' 6"-9" 26' 1/2"	10,662 Gal. Bit. Mat.	14	6.03

YEARS		TOTAL MILES	UNINCORPORATED		INCORPORATED		RURAL		URBAN	
FROM	TO		RDWY. MI.	BR. MI.	RDWY. MI.	BR. MI.	RDWY. MI.	BR. MI.	RDWY. MI.	BR. MI.
1934	1935	9.20	9.20	0.00	0.00	9.20	0.00	0.00	0.00	
1936		6.03	4.98	0.03	1.02	0.00	6.00	0.03	0.00	

REMARKS: Layout is to scale as of 1936.

