


PREPARED BY
HIGHWAY PLANNING SURVEY
IN COOPERATION WITH
U.S. PUBLIC ROADS ADMINISTRATION

STATE OF MINNESOTA
DEPARTMENT OF HIGHWAYS
ROAD LIFE STUDIES
CONSTRUCTION PROJECT LOG RECORD

CONTROL SECTION 4804
TRUNK HIGHWAY 27
COUNTY Mille Lacs
DISTRICT 38

LIMITS: N. Jct. T.H. 169 - S. Jct. T.H. 47 in Isle.



YEAR BUILT	PROJECT N ^o	DESCRIPTION		REMARKS	CODE N ^o
		TYPE	WIDTH THICKNESS		
C 1945	4804-03	Gravel Base Bit. Surf. Treat. (Mixed Prime)	27' 6"	(1) MC-1, 10000 Gal./Mi.	1
C 1946	A.F.E. 16	Spot Gravel Lifts Bit. Resurfacing Mixed Bit.	30' 6" 26' 6" Added	RT-6, 104644 Gal. Agg. 5824 C.Y.	2
M 1949	A.F.E. 4	Spot Treat. Bit. Surf. Repair	24'	RT-8&5C3, 34369 Gal. Agg. 1407 C.Y.	3
M 1951	A.F.E. 4	Spot Treat. Bit. Surf. Repair	24'	SC-4, 10821 Gal. Agg. 592 C.Y.	4
M 1952	A.F.E. 4	Spot Treat. Bit. Surf. Repair	24'	SC-4, 15530 Gal. Agg. 1526 Tons	5
M 1953	A.F.E. 604	Spot Treat. Bit. Surf. Repair	24'	SC-4, 24218 Gal. Agg. 2234 Tons	6
M 1954	A.F.E. 604	Spot Treat. Bit. Surf. Repair	24'	SC-4, 18190 Gal. Agg. 1890 Tons	7
C 1954	4804-08	Bit. Stab. Base Plant Mix Bit.	40' 12" 26' 2"		8
C 1955	A.F.E. 820 A.F.E. 819	Bit. Resurfacing Mixed Bit. 30"x46" C.M. PARCH. CURV	24' 1"	MC-3, 87516 Gal. Agg. 6961 Tons Spot Suber. corr.	9
C 1955	4804-10	Gravel Base Mixed Bit.	34' 6" 26' 2"	Added thickness	10
M 1958	A.F.E. 605	Spot Seal Coat	26'	RG-2, 18789 Gal. Agg. 678 C.Y.	11
M 1963		Light Bit Seal	26'	RS-2K, 17001 Gal. Agg. 680 C.Y.	12
C 1965	4804-11	Shoulder Grading Plant Mix Bit. Surf.	24' 3"	Rt & Lt. of rdwy. inp. over surf. inp.	13
C 1974	- 13	Pl. Mix. Bit. Surf. Gravel Shoulders	24' 2" 5'-8"		14

YEARS FROM	TOTAL TO	UNINCORPORATED		INCORPORATED		RURAL		URBAN	
		RDWY. MI.	BR. MI.	RDWY. MI.	BR. MI.	RDWY. MI.	BR. MI.	RDWY. MI.	BR. MI.

REMARKS: See Sheet N^o 1
(1) There were short exceptions on this job and gravel base thickness varied on a few short sections.

